



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Ballclay**

Code : **K.C.BA-006**

Technical Properties	
Green M.O.R. (Kgf/Cm ²)	***
Dried M.O.R. (Kgf/Cm ²)	36.03
Firing Shrinkage (1190 °C)	0.11
Firing STRENGTH (1190 °C)	780
WATER ABSORPTION	0.00
Packing	BULK & BIG BAG

Mineral Composition	

Chemical analysis	
SiO ₂	67.27
Al ₂ O ₃	20.70
Na ₂ O	0.47
K ₂ O	1.70
MgO	0.45
CaO	0.14
Fe ₂ O ₃	1.47
TiO ₂	0.68
MnO	0.00
P ₂ O ₅	0.00
SO ₃	0.61
L.O.I.	6.32
Total	***

REMARKS : FIRED COLOR , BUFF

MATERIAL , PAKING & TRANSPORTING COST TO BANDAR-ABBAS (PER KG) :

\$

Confirmed by :
KAM CERAMICS

Date :