



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Ballclay**

Code : **K.C.BA-T2008**

Technical Properties	
M.O.R. (Kg/Cm ²)	
Plasticity	
Firing Whiteness (at °C)	
Firing Shrinkage (at °C)	
Physial Form	
Packing	

Mineral Composition	

Chemical analysis	
SiO ₂	62.93
Al ₂ O ₃	23.96
Na ₂ O	1.04
K ₂ O	2.85
MgO	0.27
CaO	0.07
Fe ₂ O ₃	0.78
TiO ₂	0.75
MnO	0.01
P ₂ O ₅	0.12
SO ₃	1.72
L.O.I.	5.21
Total	99.71

Confirmed by :
KAM CERAMICS

Date :