



# KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

**BENTONITE**

Code : **K.C.BE-145**

Technical Properties	
Fired M.O.R. ( Kgf/Cm <sup>2</sup> )	*
Water of Plasticity ( % )	*
Fired color	*
wet	*
Water Absorption (%)	*
Yeild	*

Mineral Composition	
Dry M.O.R. ( Kgf/Cm <sup>2</sup> )	*
Green M.O.R. ( Kgf/Cm <sup>2</sup> )	*
Moisture (%)	*
Acide test (@20%HCL)	*
	*

Chemical analysis	
SiO2	51.30
Al2O3	16.57
Na2O	3.03
K2O	1.01
MgO	2.90
CaO	5.10
Fe2O3	3.95
TiO2	0.47
MnO	0.02
P2O5	0.22
S	0.32
L.O.I.	15.43
Total	*

Remarks :

Applications

Available Sizes

Confirmed by :  
**KAM CERAMICS**

Date :