



# KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :Bentonite

Code : K.C.BE-235

Property	Unit	Required	result
viscometer Dial Reading @ 600 rpm	cP	30,min	30 -34
Yield Point / plastic Viscosity Ratio YP/PV	*	6,Max	4.5 -6
Filterate Valume	cm3	16.0,Max	15.5 -16.3
Residue greater than 75 micrometers (200 mesh)	wt %	2.5 , Max	1.5 - 2.5
Moisture	wt %	13.0 , Max	10.0 - 13.0
Yield	m3 / tonne	16.0 Min	16.0 -16.8

Confirmed by :  
KAM CERAMICS

Date :