



# KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

BENTONITE

Code : K.C.BE-254

Physical Analysis	
Percent of Montmorillonite	*
Percent Of Montmorillonite mn 619	*
Gelling index after 8 hours	*
Gelling index after 24 hours	*
Gelling index after 2 hours	*
Percent of Moisture	*
YP/PV	*
Yield Point	*
PH	*
Swell index	*
Water Absorption Percent Next 1 Hour (%)	*
Water Absorption Percent Next 2 Hour(%)	*
Water Absorption Percent Next 4 Hour(%)	*
P%	*

Chemical analysis	
SiO2	66.64
Al2O3	9.52
Na2O	2.12
K2O	0.13
MgO	0.82
CaO	4.28
Fe2O3	2.63
TiO2	*
MnO	*
P2O5	*
SO3	*
L.O.I.	13.75
Total	*

Remarks :

Applications

Available Sizes

Confirmed by :  
KAM CERAMICS

Date :