



# KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

**Type: Bentonite**

**Code : K.C.BE-322**

| Chemical analysis              |       |
|--------------------------------|-------|
| SiO <sub>2</sub>               | 67.03 |
| Al <sub>2</sub> O <sub>3</sub> | 11.02 |
| Na <sub>2</sub> O              | 0.36  |
| K <sub>2</sub> O               | 0.34  |
| MgO                            | 2.29  |
| CaO                            | 5.54  |
| Fe <sub>2</sub> O <sub>3</sub> | 0.96  |
| TiO <sub>2</sub>               | 0.09  |
| MnO                            | 0.12  |
| SO <sub>3</sub>                | 0.12  |
| P <sub>2</sub> O <sub>5</sub>  | 0.05  |
| L.O.I                          | 12.02 |

| Producing Size             |
|----------------------------|
| LUMPS & Chips & Micronized |

**Confirmed by :  
KAM CERAMICS**

**Date :**