



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **Kaolin**

Code : **K.C.KA-001**

| Technical Properties | |
|---------------------------------|--|
| M.O.R. (Kg/Cm ²) | |
| Plasticity | |
| Firing Whiteness (at °C) | |
| Firing Shrinkage (at °C) | |
| Physial Form | |
| Packing | |

| Mineral Composition | |
|---------------------|--|
| | |
| | |
| | |
| | |
| | |

| Chemical analysis | |
|--------------------------------|-------|
| SiO ₂ | 73.13 |
| Al ₂ O ₃ | 18.57 |
| Na ₂ O | 0.43 |
| K ₂ O | 3.37 |
| MgO | 0.22 |
| CaO | 0.40 |
| Fe ₂ O ₃ | 0.58 |
| TiO ₂ | 0.56 |
| MnO | 0.01 |
| P ₂ O ₅ | 0.09 |
| SO ₃ | 0.00 |
| L.O.I. | 2.54 |
| Total | 99.90 |

| | |
|---|--------------|
| Remarks : | |
| MATERIAL PRICE PER KG : | RIALS |
| TRANSPORTING COST TO BANDAR-ABBAS PER KG : | RIALS |

Confirmed by :
KAM CERAMICS

Date :