



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **KAOLIN**

Code : **K.C.KA-018**

Technical Properties	
M.O.R. (Kgf/Cm ²)	
Plasticity (Peff.)	
Firing Whiteness (1180 °C)	
Firing Shrinkage (1180 °C)	
Physial Form	
Packing	

Mineral Composition	

Chemical analysis	
SiO ₂	59.51
Al ₂ O ₃	24.00
Na ₂ O	0.45
K ₂ O	1.65
MgO	0.24
CaO	0.33
Fe ₂ O ₃	0.34
TiO ₂	0.49
MnO	0.00
P ₂ O ₅	0.10
SO ₃	0.00
L.O.I.	6.96
Total	94.08

Confirmed by :
KAM CERAMICS

Date :