



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : KAOLIN

Code : K.C.KA-020

Technical Properties	
M.O.R. (Kgf/Cm ²)	50.00
Plasticity (Peff.)	
Firing Whiteness (1180 °C)	
Firing Shrinkage	3.24
Physial Form	
Packing	

Mineral Composition	

Chemical analysis	
SiO ₂	69.06
Al ₂ O ₃	13.46
Na ₂ O	0.72
K ₂ O	3.46
MgO	3.70
CaO	1.21
Fe ₂ O ₃	1.46
TiO ₂	0.19
MnO	0.01
P ₂ O ₅	0.06
SO ₃	0.10
L.O.I.	5.89
Total	99.32

Confirmed by :
KAM CERAMICS

Date :