



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : KAOLIN

Code : K.C.KA-101

Technical Properties	
Fired M.O.R. (Kg/Cm ²)	11.4
Water of Plasticity (%)	23.12
Firing Whiteness (1180 °C)	White
Shrinkage (%)	0.87
Water Absorption (%)	19.45
L,a,b values	93.48,0.80,3.98

Mineral Composition	

Chemical analysis	
SiO ₂	64.89
Al ₂ O ₃	31.14
Na ₂ O	0.01
K ₂ O	0.01
MgO	0.14
CaO	0.08
Fe ₂ O ₃	0.13
TiO ₂	0.38
MnO	*
P ₂ O ₅	*
S	
L.O.I.	3.33
Total	

Remarks :

Applications

Available Sizes

Confirmed by :
KAM CERAMICS

Date :