



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

KAOLIN

Code : K.C.KA-ES001N

Technical Properties	
Fired M.O.R. (Kgf/Cm ²)	146.52
Water of Plasticity (%)	25.57
Firing Whiteness (1180 °C)	White
Shrinkage (%)	1.34
Water Absorption (%)	10.29
L,a,b values	95.35,1.25,4.35

Mineral Composition	

Chemical analysis	
SiO ₂	70.94
Al ₂ O ₃	21.27
Na ₂ O	0.11
K ₂ O	0.01
MgO	0.14
CaO	0.39
Fe ₂ O ₃	0.25
TiO ₂	0.38
MnO	*
P ₂ O ₅	*
S	
L.O.I.	6.81
Total	

Remarks :

Applications

Available Sizes

Confirmed by :
KAM CERAMICS

Date :