



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : KAOLIN

Code : K.C.KA-JKF001

Technical Properties	
M.O.R. (Kg/Cm ²)	*
Plasticity (Peff.)	*
Firing Whiteness (1180 °C)	*
Firing Shrinkage (1180 °C)	*
Physial Form	*
Packing	*

Mineral Composition	

Chemical analysis	
SiO ₂	73.09
Al ₂ O ₃	16.87
Na ₂ O	4.63
K ₂ O	0.91
MgO	0.19
CaO	0.19
Fe ₂ O ₃	0.32
TiO ₂	0.55
MnO	0.0
P ₂ O ₅	*
SO ₃	*
L.O.I.	3.06
Total	

Remarks :

Applications

Avallable Sizes

Confirmed by :
KAM CERAMICS

Date :