



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : KAOLIN

Code : K.C.KA-MKCR

Technical Properties	
M.O.R. (Kg/Cm ²)	18 ± 2
Plasticity (Peff.)	28 ±1
Firing Whiteness (1200 °C)	75 ± 2
Firing Shrinkage (1200°C)	12 ± 1
Physial Form	***
Packing	***

Mineral Composition	

Chemical analysis	
SiO ₂	69± 1
Al ₂ O ₃	21± 0.5
Na ₂ O	<0.3
K ₂ O	3 ± 0.5
MgO	<0.2
CaO	<0.6
Fe ₂ O ₃	0.35
TiO ₂	<0.2
MnO	*
P ₂ O ₅	*
SO ₃	Trace
L.O.I.	5 ± 0.5
Total	***

Confirmed by :
KAM CERAMICS

Date :