



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : **KAOLIN**

Code : **K.C.KA-MSHS**

Technical Properties	
M.O.R. (Kgf/Cm ²)	
Plasticity (Peff.)	
Firing Whiteness (1180 °C)	
Firing Shrinkage (1180 °C)	
Physial Form	
Packing	

Mineral Composition	

Chemical analysis	
SiO ₂	73.86
Al ₂ O ₃	13.14
Na ₂ O	0.10
K ₂ O	4.61
MgO	0.39
CaO	0.43
Fe ₂ O ₃	4.57
TiO ₂	0.40
MnO	<0.01
P ₂ O ₅	0.12
S	0.06
L.O.I.	2.18
Total	99.86

Confirmed by :
KAM CERAMICS

Date :