



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : KAOLIN

Code : K.C.KA-NAR80

Technical Properties	
M.O.R. (Kgf/Cm ²)	*
Plasticity (Peff.)	*
Firing Whiteness (1180 °C)	*
Firing Shrinkage (1180 °C)	*
Physial Form	*
Packing	*

Mineral Composition	

Chemical analysis	
SiO ₂	68.74
Al ₂ O ₃	21.53
Na ₂ O	0.03
K ₂ O	0.01
MgO	0.06
CaO	0.85
Fe ₂ O ₃	0.24
TiO ₂	0.452
MnO	0.005
P ₂ O ₅	0.038
SO ₃	0.745
L.O.I.	7.00
Total	

Remarks :

Applications

Avallable Sizes

Confirmed by :
KAM CERAMICS

Date :