



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type : KAOLIN- BENTONITE

Code : K.C.KABE-121

Technical Properties	
M.O.R. (Kg/Cm ²)	*
Plasticity (Peff.)	*
Firing Whiteness (1180 °C)	*
Firing Shrinkage (1180 °C)	*
Physial Form	*
Packing	*

PHYSICAL PROPERTIES	
Swelling Factor (ml/2g)	11
RPM Q300	9
RPM Q600	13
Montmorilonite	46
Whiteness	75.00

Chemical analysis	
SiO ₂	60.15
Al ₂ O ₃	14.84
Na ₂ O	3.15
K ₂ O	1.46
MgO	1.53
CaO	2.84
Fe ₂ O ₃	1.06
TiO ₂	*
MnO	*
P ₂ O ₅	*
S	*
L.O.I.	10.61
Total	

Remarks :

Applications

Available Sizes

Confirmed by :
KAM CERAMICS

Date :