



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

TALC

Code : K.C.TA-172

Technical Properties	
M.O.R. (Kg/Cm ²)	*
Plasticity (Peff.)	*
Firing Whiteness (1180 °C)	*
Firing Shrinkage (1180 °C)	*
Physial Form	*
Packing	*

Mineral Composition	

Chemical analysis	
SiO ₂	48.01
Al ₂ O ₃	4.20
Na ₂ O	0.09
K ₂ O	0.30
MgO	21.87
CaO	8.04
Fe ₂ O ₃	10.17
TiO ₂	0.153
MnO	0.167
P ₂ O ₅	0.031
SO ₃	
L.O.I	
total	*

Remarks :

Applications

Available Sizes

Confirmed by :
KAM CERAMICS

Date :