



# KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045  
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

TALC

Code : K.C.TA-175

Technical Properties	
M.O.R. ( Kg/Cm <sup>2</sup> )	*
Plasticity ( Peff. )	*
Firing Whiteness ( 1180 °C )	*
Firing Shrinkage ( 1180 °C )	*
Physial Form	*
Packing	*

Mineral Composition	

Chemical analysis	
SiO <sub>2</sub>	40.98
Al <sub>2</sub> O <sub>3</sub>	18.31
Na <sub>2</sub> O	0.05
K <sub>2</sub> O	0.41
MgO	21.08
CaO	0.82
Fe <sub>2</sub> O <sub>3</sub>	4.04
TiO <sub>2</sub>	0.98
MnO	0.03
P <sub>2</sub> O <sub>5</sub>	0.79
S	<0.07
L.O.I	12.44
total	*

Remarks :

Applications

Available Sizes

Confirmed by :  
KAM CERAMICS

Date :