



KAM CERAMICS

INDUSTRIAL TRADING JLT

Unit No. 1404, HDS Tower, Cluster F, Jumeirah Lakes Towers Dubai - UAE. Tel: +971 4 4541044 Fax: +971 4 4541045
www.kam-ceramics.com Email: k.m.moshrefi@kam-ceramics.com

Type :

TALC

Code : K.C.TA-177

Technical Properties	
M.O.R. (Kg/Cm ²)	*
Plasticity (Peff.)	*
Firing Whiteness (1180 °C)	*
Firing Shrinkage (1180 °C)	*
Physial Form	*
Packing	*

Mineral Composition	
*	*
*	*
*	*
*	*
*	*

Chemical analysis	
SiO ₂	46.00
Al ₂ O ₃	2.00
Na ₂ O ₃	0.40
K ₂ O	0.08
MgO	29.60
CaO	6.38
Fe ₂ O ₃	0.19
TiO ₂	0.02
MnO	0.002
P ₂ O ₅	*
SO ₃	*
L.O.I	14.36
total	*

Confirmed by :
KAM CERAMICS

Date :